


## SEAT PRESSURE/TEMPERATURE RATINGS

Seat	Temperature (°F)	2"-36" Pressure (PSIG)
EPDM	-20	225
	100	225
	200	225
	250	75
	300	50
Buna-N	0	225
	100	225
	180	225
	200	75
	220	50
FKM/ Viton®	-10	225
	100	225
	250	225
	325	100
	360	50

## PRESSURE VS. TEMPERATURE CHART

Resilient Seated BFV 2"-36"



DESCRIPTION:

Pressure Temperature Curve - 150 Class Resilient Seated BFV

DATE:

05.13.2024

DWG:

TS-TD0013-A



McWane Plant & Industrial  
1201 Vanderbilt Road  
Birmingham, AL 35234